



Sơn Nippon  
Sơn Đẹp Cũng Đẹp

Ref. No. : PDS-0405-EN  
Version No. : 3  
Updated Date : 17.12.18

## PRODUCT DATA SHEET

# NIPPON TEXKOTE

<b>Description</b>	Special Acrylic Emulsion giving three dimensional polymeric surface coating by spraying.
<b>Type</b>	Acrylic Emulsion
<b>Uses</b>	As a decorative / protective texture body coat for architectural surfaces under Interior and exterior condition such as: - Cement plasters                      - Brickworks                      - Fiberboards ... - Concrete                                      - Primed wood
<b>Finish</b>	Matt Color: White
<b>Features</b>	<ul style="list-style-type: none"> <li>- Excellent mechanical film properties such as film hardness, adhesion, scratch an abrasion resistance</li> <li>- Excellent algae and fungi resistance</li> <li>- Resistance to mud cracking tendency</li> <li>- Combination with topcoat, Nippon Texkote provides outstanding weathering property, high degree water repellency, good alkali resistance and Anti-dirt collection</li> <li>- Easy application with variation in pattern and shape of the film by means of application method</li> </ul>
<b>APPLICATION DATA</b>	
<b>Surface Preparation</b>	Surface preparation should thoroughly done: Treatment with ANTI-FUNGUS SOLUTION is necessary for fungus growth area. Surface should be clean, dry and stable before application. For new cement substrate, minimum cured through a time period for at least 21 days is required. Observed the moisture content prior to painting: (By Sovereign Moisture meter) Masonry : Below 6% Wood : Below 10%
<b>Application Methods</b>	Air spray
<b>Paint Consumption</b>	Theoretical: 0.7 to 1.5 m <sup>2</sup> /liter depending on pattern desired
<b>Dilution</b>	For better result, no dilution is recommended. If need, use clean water, not more than 3%.

## NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam

Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

[www.nipponpaint.com](http://www.nipponpaint.com)

# NIPPON TEXKOTE

<b>Spray Application</b>	<u>Air Spray</u>
	Delivery Pressure (kg/cm <sup>2</sup> ) 2.5 - 4.5
	Tip size at 60° angle 4.5 or 6 mm
	Spray distance from substrate 1 foot
	Dilution 3% maximum
	To obtain "head-cut" pattern, roller should be used to press down the paint film when it is in semi-dry condition (about 10 - 15 minutes after application)
<b>Overcoating Time</b>	72 hours. Minimum
<b>Cleaning</b>	Wash all equipment immediately after use with clean water
<b>Storage</b>	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.
<b>Packing</b>	18 Liters
<b>Precaution</b>	Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid directly contacting with sensitive skin. Use appropriate protective equipment.
<b>NOTE</b>	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales &amp; Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>

## NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam

Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

[www.nipponpaint.com](http://www.nipponpaint.com)