



PRODUCT DATA SHEET

ODOUR-LESS ALL-IN-1

Description	Nippon ODOUR-LESS ALL-IN-1 is an environmentally favorable product formulated with low VOCs (Volatile Organic Compounds) for Interior use. Specially formulated with a solvent-free Polymer, it limits air pollutants and has an extremely low odour during application and drying. It is especially ideal for use in eco-sensitive commercial and residential areas with high frequency human traffic such as hospitals, schools, residential buildings and hotels.
Type	Modified Acrylic Copolymer Emulsion
Uses	It is ideal for interior walls and ceilings such as: <ul style="list-style-type: none"> - Cement plasters - Brickworks - Gypsum board - Concrete - Primed wood - Fiberboards ...
Finish	Soft Matt or Sheen Colour: Wide range of attractive colours as per colour card. Special colours on request.
Features	<ul style="list-style-type: none"> - Environmental friendly interior emulsion - Ultra-low VOCs (containing < 25g/L VOC, meeting the VOC requirement) - Extremely low odour during application and drying - Non-toxic, does not contain lead, mercury and heavy metals - Anti-fungus & algae properties - Excellent coverage and hiding power - Long lasting colors - Washable - Easy application, less splattering - Excellent adhesion
APPLICATION DATA	
Surface Preparation	<p>Surface must be clean, dry, and stable.</p> <p><u>Suggested Treatment:</u></p> <p><u>Dirt/Powder:</u> Clean with damp cloth and remove loose powder. Mild detergent may be used.</p> <p><u>Old Paint/Plaster/Skimcoat:</u> Unstable old film / substrate should be removed by chisel, scraper, power grinder whichever is appropriate. Uneven substrates must be re-plastered with an approved putty / skimcoat.</p>

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

ODOUR-LESS ALL-IN-1

	<p>Moisture: High moisture will cause paint defect. Observe the following level prior to painting:</p> <ul style="list-style-type: none"> - Masonry : below 6% by Sovereign 1150 Moisture meter below 16% by Protimeter Mini BLD 2000 Moisture meter below 60% by Lutron MS-7003 Moisture meter <p>All water seepage must be checked and repaired.</p> <p>Algae/Fungus: Remove by chisel or scraper and treat with NIPPON ANTI- FUNGUS SOLUTION. Rinse again with clean water and dry.</p> <p>Oil/Grease: Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace.</p>								
Application Methods	Brush, roller or airless spray								
Paint Consumption	Theoretical: 12.0 m ² / liter (30 microns DFT)								
Dilution	Use clean water Roller & brush - 20% maximum Airless Spray - 10% maximum								
Spray Application	<table style="width: 100%; border-collapse: collapse;"> <tr> <td></td> <td style="text-align: right;"><u>Airless Spray</u></td> </tr> <tr> <td>Delivery Pressure (kg/cm²)</td> <td style="text-align: right;">120 - 150</td> </tr> <tr> <td>Tip size at 60° angle</td> <td style="text-align: right;">0.017"</td> </tr> <tr> <td>Dilution</td> <td style="text-align: right;">10% maximum</td> </tr> </table>		<u>Airless Spray</u>	Delivery Pressure (kg/cm ²)	120 - 150	Tip size at 60° angle	0.017"	Dilution	10% maximum
	<u>Airless Spray</u>								
Delivery Pressure (kg/cm ²)	120 - 150								
Tip size at 60° angle	0.017"								
Dilution	10% maximum								
Recommended Painting System	<ul style="list-style-type: none"> - 2- 3 coats SKIMCOAT NỘI THẤT - 1 coat ODOUR-LESS SEALER - 2 coats ODOUR-LESS ALL IN 1 								
Recommended Film Thickness	30 - 40 microns DFT (Dry Film Thickness) per coat for standard application								
Drying Time	Surface dry - 30 minutes at 30°C								
Overcoating Time	2 hours. Minimum								
Cleaning	Wash all equipment immediately after use with clean water								
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.								
Packing	1 Liter and 5 Liters								
Precaution	Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.								
NOTE	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>								

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

 www.nipponpaint.com