

ODOUR-LESS SEALER

	<p><u>Algae/Fungus:</u> Remove by chisel or scraper and treat with NIPPON ANTI-FUNGUS SOLUTION. Rinse again with clean water and dry.</p> <p><u>Hairline cracks:</u> Fill cracks with solvent-based filler or non-water soluble material.</p>								
Application Methods	Brush, roller or airless spray								
Paint Consumption	Theoretical: 12.0 m ² /Liter (30 microns DFT)								
Dilution	<p>Use clean water</p> <p>Roller & brush - 20% maximum</p> <p>Airless Spray - 10% maximum</p>								
Spray Application	<table style="width: 100%; border-collapse: collapse;"> <tr> <td></td> <td style="text-align: center;"><u>Airless Spray</u></td> </tr> <tr> <td>Delivery Pressure (kg/cm²)</td> <td style="text-align: center;">120 - 150</td> </tr> <tr> <td>Tip size at 60° angle</td> <td style="text-align: center;">0.017"</td> </tr> <tr> <td>Dilution</td> <td style="text-align: center;">10% maximum</td> </tr> </table>		<u>Airless Spray</u>	Delivery Pressure (kg/cm ²)	120 - 150	Tip size at 60° angle	0.017"	Dilution	10% maximum
	<u>Airless Spray</u>								
Delivery Pressure (kg/cm ²)	120 - 150								
Tip size at 60° angle	0.017"								
Dilution	10% maximum								
Recommended Film Thickness	30 - 40 microns DFT (Dry Film Thickness) per coat for standard application								
Drying Time	Surface dry - 10 minutes at 30°C								
Overcoating Time	2 hours. Minimum								
Cleaning	Wash all equipment immediately after use with clean water								
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.								
Packing	5 Liters & 18 Liters								
Precaution	Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid directly contacting with sensitive skin. Use appropriate protective equipment.								
NOTE	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>								

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam

Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

 www.nipponpaint.com