

Ref. No.: PDS-0335-EN Version No.: 5

Updated Date: 17.12.18

PRODUCT DATA SHEET

SUPER MATEX

Description	Nippon SUPER MATEX is formulated to resist cement alkali material on exterior masonry surfaces. It has excellent anti-fungus property. It gives good coverage and is easy to use.		
·			
Туре	Modified Acrylic Emulsion		
Uses	Coating for exterior surfaces such as:		
	- Cement plasters - Concrete - Brickworks		
Finish	Matt		
	Colour: Wide range of colours as per colour card. Special colours on request.		
Features	- Resists deterioration by fresh cement		
	- Anti-fungus / algae property		
	- High opacity for good coverage and easy application		
	- Washable with water and/or mild detergents		
	- Good weather resistance		
APPLICATION DATA			
Surface Preparation	Surface must be clean, dry, and stable.		
	Suggested Treatment:		
	<u>Dirt/Powder:</u> High pressure water wash. Mild detergent may be used. For very powdery		
	surface, apply a coat of HITEX 5180 SEALER after cleaning. Old Paint/Plaster/Skimcoat: Unstable old film / substrate should be removed by chisel, scraper, power grinder whichever is appropriate. Uneven substrates must be re-plastered with an approved putty / skimcoat.		
	Moisture: High moisture will cause paint defect. Observe the following level prior to		
	painting:		
	- Masonry : below 6% by Sovereign 1150 Moisture meter		
	below 16% by Protimeter Mini BLD 2000 Moisture meter		
	below 60% by Lutron MS-7003 Moisture meter		
	All water seepage must be checked and repaired.		
	Algae/Fungus: Remove by high pressure wash or by chisel, scraper and treat with		
	NIPPON ANTI- FUNGUS SOLUTION. Rinse again with clean water and dry.		
	Oil/Grease: Clean off with mild detergent and a little solvent if necessary. Wash thoroughly		
	to remove all trace.		

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 - 3836586 (8 lines), Fax: (84).251.3836346 - 3836349



SUPER MATEX

Application Methods	Brush, roller or airless spray		
Paint Consumption	Theoretical: 12.7 m ² /liter (30 microns DFT)		
Dilution	Not more than 20% with clean water if required		
	Roller & brush	- 20% maximum	
	Airless Spray	- 10% maximum	
Spray Application		Airless Spray	
	Delivery Pressure (kg/cm²)	120 - 150	
	Tip size at 60° angle	0.017"	
	Dilution	10% maximum	
Recommended	- 2 - 3 coats WEATHERGARD SKIMCOAT		
Painting System	- 1 coat SUPER MATEX SEALER or WEATHERGARD SEALER - 2 coats SUPER MATEX		
Recommended Film	30 – 40 microns DFT (Dry Film Thickness) per coat for standard application		
Thickness			
Drying Time	Surface dry - 10 minutes at 30°C		
Overcoating Time	2 hours. Minimum		
Cleaning	Wash all equipment immediately after use with clean water		
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature		
	between 5 to 40°C.		
Packing	5 Liters & 18 Liters		
Precaution	Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid		
	direct contact with sensitive skin. Use appropriate protective equipment.		
NOTE	The information given applies to the product and its performance under specific test conditions. Due to the varie		
	circumstances beyond our control under which the product may be applied, for specific application, please contact		
	Nippon Paint Sales & Marketing Dept	. We reserve the right to modify our product data sheet without further notice.	

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836349

