

Ref. No. : PDS-0356-EN Version No. : 7 Updated Date : 17.12.18

#### PRODUCT DATA SHEET

# WEATHERGARD

A high-performance water-based paint that possesses superior exterior durability with water resistance and solar reflective properties.
Modified Acrylic Emulsion
Premium grade emulsion with excellent protective and decorative functions for all exterior masonry surfaces such as:         - Cement plasters       - Concrete       - Brickworks
Sheen Colour: Wide range of decorative colours as per colour card. Special colours on request.
<ul> <li>Excellent weathering resistance and long lasting colour.</li> <li>High solar energy reflection, less heat build-up results in less power consumption for air- conditioning – energy saving.</li> <li>Good water resistant</li> <li>Excellent resistance to fungus and algae growth</li> <li>Excellent washability</li> <li>Excellent to Alkaline &amp; Efflorescence properties</li> <li>Good adhesion on stable substrates</li> <li>Easy apply with good flow &amp; leveling properties</li> <li>Low VOCs (containing &lt; 50g/L VOC, meeting the VOC requirement)</li> <li>Non-toxic, does not contain lead, mercury and heavy metals</li> </ul>
Surface must be clean, dry, and stable. <u>Suggested Treatment:</u> <u>Dirt/Powder:</u> High pressure water wash. Mild detergent may be used. For very powdery surface, apply a coat of HITEX 5180 SEALER after cleaning. <u>Old Paint/Plaster/Skimcoat:</u> Unstable old film / substrate should be removed by chisel, scraper, power grinder whichever is appropriate. Uneven substrates must be re-plastered with an approved putty / skimcoat. <u>Moisture:</u> High moisture will cause paint defect. Observe the following level prior to painting: - Masonry : below 6% by Sovereign 1150 Moisture meter below 16% by Protimeter Mini BLD 2000 Moisture meter

### NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349



# WEATHERGARD

	below 60% by Lutron MS-7003 Moisture meter All water seepage must be checked and repaired. <u>Algae/Fungus:</u> Remove by high pressure wash or by chisel, scraper and treat with NIPPON ANTI- FUNGUS SOLUTION. Rinse again with clean water and dry. <u>Oil/Grease:</u> Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace.
Application Methods	Brush, roller or airless spray
Paint Consumption	Theoretical: 10.0 m <sup>2</sup> / liter ( At 40µm DFT)
Dilution	Not more than 10% of clean water if requiredRoller & brush- 10% maximumAirless Spray- 5% maximum
Spray Application	Airless SprayDelivery Pressure (kg/cm²)120 - 150Tip size at 60° angle0.017"Dilution5% maximum
Recommended Painting System	<ul> <li>- 2 - 3 coats WEATHERGARD SKIMCOAT</li> <li>- 1 coat WEATHERGARD SEALER</li> <li>- 2 coats WEATHERGARD</li> </ul>
Recommended Film Thickness	40 – 50 microns DFT (Dry Film Thickness) per coat for standard application
Drying Time	Surface dry - 30 minutes at 30°C
Overcoating Time	2 hours. Minimum
Post Treatment	As the paint film is elastic, masking tapes used to protect surfaces not to be painted, e.g. door and window frames, should be removed with a knife or cutter.
Cleaning	Wash all equipment immediately after use with clean water
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.
Packing	1 Liter, 5 Liters & 18 Liters
Precaution	Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.
NOTE	The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.

### NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

