



Sơn Nippon
Sơn Đẹp Cũng Đẹp

Ref. No. : PDS-0359-EN
Version No. : 3
Update Date : 17.12.18

PRODUCT DATA SHEET

WEATHERGARD PLUS+

Description	A high-performance water-based paint that possesses superior exterior durability with water proofing and very good dirt pick up resistance.
Type	Pure Acrylic Emulsion with Micro Gel Technology
Uses	Premium grade emulsion with excellent protective and decorative functions for all exterior masonry surfaces such as: - Cement plasters - Concrete - Brickworks...
Finish	Sheen Colour: Wide range of decorative colours as per colour card. Special colours on request.
Features	<ul style="list-style-type: none"> - Excellent weathering resistance and long lasting colour - Very good dirt pick up resistance - Good wash ability and water proofing - Good water streak mark resistance - High solar energy reflection, less heat build-up results in less power consumption for air-conditioning – energy saving - Excellent resistance to fungus and algae growth - Excellent to Alkaline & Efflorescence properties - Good adhesion on stable substrates - Easy apply with good flow & leveling properties - Low VOCs (containing < 30g/L VOC, meeting the VOC requirement) - APEO free, Non-toxic, does not contain lead, mercury and heavy metals
APPLICATION DATA	
Surface Preparation	<p>Surface must be clean, dry, and stable.</p> <p><u>Suggested Treatment:</u></p> <p><u>Dirt/Powder:</u> High pressure water wash. Mild detergent may be used. For very powdery surface, apply a coat of HITEX 5180 SEALER after cleaning.</p> <p><u>Old Paint/Plaster/Skimcoat:</u> Unstable old film / substrate should be removed by chisel, scraper, and power grinder whichever is appropriate. Uneven substrates must be re-plastered with an approved putty / skimcoat.</p> <p><u>Moisture:</u> High moisture will cause paint defect. Observe the following level prior to painting:</p> <ul style="list-style-type: none"> - Masonry : below 6% by Sovereign 1150 Moisture meter

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

WEATHERGARD PLUS+

	<p style="text-align: center;">below 16% by Protimeter Mini BLD 2000 Moisture meter below 60% by Lutron MS-7003 Moisture meter</p> <p>All water seepage must be checked and repaired.</p> <p><u>Algae/Fungus:</u> Remove by high pressure wash or by chisel, scraper and treat with NIPPON ANTI- FUNGUS SOLUTION. Rinse again with clean water and dry.</p> <p><u>Oil/Grease:</u> Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace.</p>
Application Methods	Brush, roller or airless spray
Paint Consumption	Theoretical: 10.0 m ² / liter (At 40μm DFT)
Dilution	<p>Not more than 10% of clean water if required</p> <p>Roller & brush - 10% maximum</p> <p>Airless Spray - 5% maximum</p>
Spray Application	<p style="text-align: right;"><u>Airless Spray</u></p> <p>Delivery Pressure (kg/cm²) 120 - 150</p> <p>Tip size at 60° angle 0.017"</p> <p>Dilution 5% maximum</p>
Recommended Painting System	<ul style="list-style-type: none"> - 2 - 3 coats WEATHERGARD SKIMCOAT - 1 coat WEATHERGARD SEALER - 2 coats WEATHERGARD PLUS+
Recommended Film Thickness	40 – 50 microns DFT (Dry Film Thickness) per coat for standard application
Drying Time	Surface dry - 30 minutes at 30°C
Over coating Time	2 hours. Minimum
Post Treatment	As the paint film is elastic, masking tapes used to protect surfaces not to be painted, e.g. door and window frames, should be removed with a knife or cutter.
Cleaning	Wash all equipment immediately after use with clean water
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.
Packing	1 Liter, 5 Liters & 18 Liters
Precaution	Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.
NOTE	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

 www.nipponpaint.com