

#### PRODUCT DATA SHEET

# VATEX

Description	VATEX is a quality paint for decoration and protection of masonry surfaces.			
Туре	Acrylic Copolymer Emulsion			
Uses	It is ideal for interior walls such as:			
	- Cement plasters	- Brickworks	- Gypsum board	
	- Concrete	- Primed wood	- Fiberboards	
Finish	Matt			
	Colour : Wide range of attractive colours as per colour card			
Features	- Economical			
	- Easy application			
	- Good coverage & hiding power			
	- Anti-fungus & algae properties			
	<ul> <li>Does not contain Lead, Mercury and heavy metals</li> <li>Comply with National technical regulation QCVN 08:2020/BCT on the limits of Lead content in paints.</li> </ul>			
APPLICATION DATA	1			
Surface Preparation	Surface must be clean, dry, and stable.			
	Suggested Treatment:			
	Dirt/Powder: Clean with used.	Powder: Clean with damp cloth and remove loose powder. Mild detergent may be		
	<u>Old Paint/Plaster/Skimcoat:</u> Unstable old film / substrate should be removed by chisel, scraper, power grinder whichever is appropriate. Uneven substrates must be re-plastered with an approved putty / skimcoat.			
	Moisture: High moisture will cause paint defect. Observe the following level prior to painting:			
	- Masonry: below 16% by Protimeter Mini BLD 2000 Moisture meter			
	below 60% by Lutron MS-7003 Moisture meter			
	All water seepage must be checked and repaired.			
	<u>Algae/Fungus:</u> Remove by chisel or scraper and treat with ANTI - FUNGUS SOLUTION. Rinse again with clean water and dry.			
	Oil/Grease: Clean off with to remove all trace.	h mild detergent and a little sol	lvent if necessary. Wash thoroughly	
Application Methods	Brush, roller or airless spray			

## NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349



## VATEX

Paint Consumption	Theoretical: 8.3 - 11.0 m <sup>2</sup> /liter (30 - 40 microns DFT)		
Dilution	Use clean water		
	Roller & brush	- 20% maximum	
	Airless Spray	- 10% maximum	
Spray Application		Airless Spray	
	Delivery Pressure (kg/cm <sup>2</sup> )	120 - 150	
	Tip size at 60° angle	0.017"	
	Dilution	10% maximum	
Recommended	- 1 - 2 coats NIPPON INTERIOR PUTTY		
Painting System	- 1 coat MATEX SEALER		
	- 2 coats VATEX		
Recommended Film Thickness per coat	30 - 40 microns DFT (Dry Film Thickness) per coat for standard application		
Drying Time	Surface dry - 10 minutes at 30°C		
Overcoating Time	2 hours. Minimum based on normal conditions.		
Cleaning	Wash all equipment immediately after use with clean water		
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.		
Packing	4.8 Kgs & 17 Liters Containers		
Precaution	Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc. The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc. Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.		
NOTE	The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.		

#### NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

