

Version No.: 1 Updated Date: 01.07.24

#### PRODUCT DATA SHEET

# **NIPPON INTERIOR PUTTY**

Description	Putty for patching and smoothening of interior wall.		
Uses	NIPPON INTERIOR PUTTY is used for interior substrates such as:		
	- Cement plasters - Concrete	e - Brickworks	
Finish	Matt/ White		
Features	- Easy application		
	- Easy sanding		
	- Create a very smooth surface		
APPLICATION DATA			
Surface Preparation	Ensure the surface is clean and stable.		
	- Masonry: below 16% by Protimeter Mini I	BLD 2000 Moisture meter	
	below 60% by Lutron MS-7003 Moisture meter		
	Extremely dry and absorbent substrates s NIPPON INTERIOR PUTTY	hould be moistened with water before applying	
Application Methods	Use trowel to apply NIPPON INTERIOR I depend on the surface.	PUTTY on the surface with thickness of 1 mm	
	Wait for 16 hours or until the surface is par thickness.	rtially settled then apply a second coat of similar	
	Sanding the surface to give a smooth finish	h.	
Paint Consumption	Theoretical: 30 - 40 m <sup>2</sup> /bag (40Kg) depend	d on thickness applied	
Mixing Instruction	Mix 01 bag NIPPON INTERIOR PUTTY wir or adequate mixing equipment to mix for 5	th 14 - 16 liters of water (Use a mixer if available - 10 minutes).	
	Add powder to water to avoid lumpiness.		
	Allow the mixture to stand for about 10 mir	nutes then mix again until homogenous.	
	Ready plaster should be used in 2 hours a	fter mixing.	
Cleaning	Wash all equipment immediately after use	with clean water	
Storage		with moisture and water, keep the bags tightly ed place at temperature between 5 to 40°C.	
Packing	40 Kgs/Bag		

# NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836349



# **NIPPON INTERIOR PUTTY**

Precaution	Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc.  The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc.	
	Do not use NIPPON INTERIOR PUTTY on unstable painted surfaces, water soluble plasters or smoothening floors.	
	Do not apply NIPPON INTERIOR PUTTY when the temperature is below 10°C & moisture is over 85%.	
NOTE	The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.	

# NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836349

