

WP 200

	<p>All water seepage must be checked and repaired.</p> <p><u>Algae/Fungus:</u> Remove by high pressure wash or by chisel, scraper and treat with ANTI-FUNGUS SOLUTION. Rinse again with clean water and dry.</p> <p><u>Oil/Grease:</u> Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace.</p>								
Application Methods	Brush, roller or airless spray								
Paint Consumption	Theoretical: 7.0 m ² / Kg (At 50 µm DFT)								
Dilution	No dilution needed.								
Spray Application	<table style="width: 100%; border: none;"> <tr> <td></td> <td style="text-align: right;"><u>Airless Spray</u></td> </tr> <tr> <td>Delivery Pressure (kg/cm²)</td> <td style="text-align: right;">120 - 150</td> </tr> <tr> <td>Tip size at 60° angle</td> <td style="text-align: right;">0.017"</td> </tr> <tr> <td>Dilution</td> <td style="text-align: right;">5% maximum</td> </tr> </table>		<u>Airless Spray</u>	Delivery Pressure (kg/cm ²)	120 - 150	Tip size at 60° angle	0.017"	Dilution	5% maximum
	<u>Airless Spray</u>								
Delivery Pressure (kg/cm ²)	120 - 150								
Tip size at 60° angle	0.017"								
Dilution	5% maximum								
Recommended Painting System	2 coats WP 200								
Recommended Film Thickness per coat	50 – 60 microns DFT (Dry Film Thickness) per coat for standard application								
Drying Time	Surface dry: 30 minutes at 30°C								
Overcoating Time	2 hours. Minimum based on normal conditions.								
Post Treatment	As the paint film is elastic, masking tapes used to protect surfaces not to be painted, e.g. door and window frames, should be removed with a knife or cutter after painting.								
Cleaning	Wash all equipment immediately after use with clean water								
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.								
Packing	6 Kgs & 20 Kgs Containers								
Precaution	<p>Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc.</p> <p>The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc.</p> <p>Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid directly contacting with sensitive skin. Use appropriate protective equipment.</p>								
NOTE	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>								

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
 Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

 www.nipponpaint.com