

PRODUCT DATA SHEET

MATEX SẮC MÀU DỊU MẮT

Description	MATEX SẮC MÀU DỊU MẮT is an emulsion paint that is specially formulated for easy application. It provides an attractive yet uniform matt finish with high opacity.
Type	A multi-purpose Acrylic Copolymer Emulsion
Uses	Decorative and protective coat for interior surfaces such as: - Cement plasters - Gypsum board - Fiberboards ... - Concrete
Finish	Matt Colour: Wide range of cool and modern colours.
Features	- Good hiding power - Good flow & leveling - Excellent touch-up property - Anti-fungus - Does not contain Lead, Mercury and heavy metals - Ultra-low VOCs (containing < 25g/L VOC, meeting the VOC requirement) - Green Label Certificate - Comply with National technical regulation QCVN 08:2020/BCT on the limits of Lead content in paints. 

APPLICATION DATA

Surface Preparation	Surface must be clean, dry, and stable. <u>Suggested Treatment:</u> <u>Dirt/Powder:</u> Clean with damp cloth and remove loose powder. Mild detergent may be used. <u>Old Paint/Plaster/Skimcoat:</u> Unstable old film / substrate should be removed by chisel, scraper, power grinder whichever is appropriate. Uneven substrates must be re-plastered with an approved putty / skimcoat. <u>Moisture:</u> High moisture will cause paint defect. Observe the following level prior to painting: - Masonry: below 16% by Protimeter Mini BLD 2000 Moisture meter below 60% by Lutron MS-7003 Moisture meter All water seepage must be checked and repaired.
----------------------------	--

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

MATEX SẮC MÀU DỊU MÁT

	<u>Algae/Fungus</u>: Remove by chisel or scraper and treat with ANTI - FUNGUS SOLUTION. Rinse again with clean water and dry. <u>Oil/Grease</u>: Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace.
Application Methods	Brush, roller or airless spray
Coverage	Theoretical: 8.3 - 11.0 m ² /liter (30 - 40 microns DFT)
Dilution	Use clean water Roller & brush - 20% maximum Airless Spray - 10% maximum
Spray Application	<u>Airless Spray</u> Delivery Pressure (kg/cm²) 120 - 150 Tip size at 60° angle 0.017" Dilution 10% maximum
Recommended Painting System	- 1 - 2 coats NIPPON INTERIOR PUTTY - 1 coat MATEX SEALER or ODOUR-LESS SEALER - 2 coats MATEX SẮC MÀU DỊU MÁT
Recommended Film Thickness	30 - 40 microns DFT (Dry Film Thickness) per coat for standard application
Drying Time	Surface dry: 30 minutes at 30°C
Overcoating Time	2 hours. Minimum based on normal conditions.
Cleaning	Wash all equipment immediately after use with clean water
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.
Packing	5 Liters & 17 Liters Containers
Precaution	Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc. The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc. Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.
NOTE	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
 Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com