

PRODUCT DATA SHEET

ODOUR-LESS CHÙI RỬA VƯỢT TRỘI & KHÁNG KHUẨN

<p>Description</p>	<p>ODOUR-LESS CHÙI RỬA VƯỢT TRỘI & KHÁNG KHUẨN is specially formulated product with easy clean performance and anti-bacterial properties. It resists stains and stains on painted surface can be cleaned easily.</p> <p>ODOUR-LESS CHÙI RỬA VƯỢT TRỘI & KHÁNG KHUẨN is effective against many types of bacteria when existing on wall such as E. coli, Staphylococcus Aureus, Salmonella typhimurium, Shigella flexneri, Pseudomonas aeruginosa, Klebsiella pneumoniae, Listeria monocytogenes which cause variety of infection in human.</p> <p>So you'll get a beautiful rich finish for walls that looks good & lasts longer.</p>
<p>Type</p>	<p>Modified Acrylic Copolymer Emulsion</p>
<p>Uses</p>	<p>It is ideal for interior walls and ceilings such as:</p> <ul style="list-style-type: none"> - Cement plasters - Brickworks - Gypsum board - Concrete - Primed wood - Fiberboards ...
<p>Finish</p>	<p>Soft Matt Colour: Wide range of attractive colours as per colour card. Special colours on request.</p>
<p>Features</p>	<ul style="list-style-type: none"> - Stains on ODOUR-LESS CHÙI RỬA VƯỢT TRỘI & KHÁNG KHUẨN can be cleaned easily - Excellent washability. - Anti-bacterial (effective against common bacteria when existing on wall such as E. coli, Staphylococcus Aureus, Salmonella typhimurium, Shigella flexneri, Pseudomonas aeruginosa, Klebsiella pneumoniae, Listeria monocytogenes) - Long lasting colors - Good Alkaline & Water resistance - Excellent coverage and hiding power - Almost no odour during application and after drying - Does not contain Lead, Mercury and heavy metals - Ultra-low VOCs (containing below 25g/L, meeting the VOC requirement) - Green Label Certificate - Comply with National technical regulation QCVN 08:2020/BCT on the limits of Lead content in paints. - NOTE: ODOUR-LESS CHÙI RỬA VƯỢT TRỘI & KHÁNG KHUẨN serves to reduce the transmission of bacteria through inactivation process on painted surface. It does not warranty users' immunity to bacteria.



NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

ODOUR-LESS CHÙI RỬA VƯỢT TRỘI & KHÁNG KHUẨN

APPLICATION DATA									
Surface Preparation	<p>Surface must be clean, dry, and stable.</p> <p>Suggested Treatment:</p> <p><u>Dirt/Powder:</u> Clean with damp cloth and remove loose powder. Mild detergent may be used.</p> <p><u>Old Paint/Plaster/Skimcoat:</u> Unstable old film / substrate should be removed by chisel, scraper, power grinder whichever is appropriate. Uneven substrates must be re-plastered with an approved putty / skimcoat.</p> <p><u>Moisture:</u> High moisture will cause paint defect. Observe the following level prior to painting:</p> <ul style="list-style-type: none"> - Masonry: below 16% by Protimeter Mini BLD 2000 Moisture meter <li style="padding-left: 40px;">below 60% by Lutron MS-7003 Moisture meter <p>All water seepage must be checked and repaired.</p> <p><u>Algae/Fungus:</u> Remove by chisel or scraper and treat with ANTI - FUNGUS SOLUTION. Rinse again with clean water and dry.</p> <p><u>Oil/Grease:</u> Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace.</p>								
Application Methods	Brush, roller or airless spray								
Paint Consumption	Theoretical: 9.0 - 12.0 m ² / liter (30 - 40 microns DFT)								
Dilution	<p>Use clean water</p> <table style="width: 100%; border: none;"> <tr> <td style="width: 60%;">Roller & brush</td> <td style="text-align: right;">- 20% maximum</td> </tr> <tr> <td>Airless Spray</td> <td style="text-align: right;">- 10% maximum</td> </tr> </table>	Roller & brush	- 20% maximum	Airless Spray	- 10% maximum				
Roller & brush	- 20% maximum								
Airless Spray	- 10% maximum								
Spray Application	<table style="width: 100%; border: none;"> <tr> <td></td> <td style="text-align: right;"><u>Airless Spray</u></td> </tr> <tr> <td>Delivery Pressure (kg/cm²)</td> <td style="text-align: right;">120 - 150</td> </tr> <tr> <td>Tip size at 60° angle</td> <td style="text-align: right;">0.017"</td> </tr> <tr> <td>Dilution</td> <td style="text-align: right;">10% maximum</td> </tr> </table>		<u>Airless Spray</u>	Delivery Pressure (kg/cm ²)	120 - 150	Tip size at 60° angle	0.017"	Dilution	10% maximum
	<u>Airless Spray</u>								
Delivery Pressure (kg/cm ²)	120 - 150								
Tip size at 60° angle	0.017"								
Dilution	10% maximum								
Recommended Painting System	<ul style="list-style-type: none"> - 1 - 2 coats NIPPON INTERIOR PUTTY - 1 coat ODOUR-LESS SEALER - 2 coats ODOUR-LESS CHÙI RỬA VƯỢT TRỘI & KHÁNG KHUẨN 								
Recommended Film Thickness per coat	30 - 40 microns DFT (Dry Film Thickness) per coat for standard application								
Drying Time	Surface dry: 30 minutes at 30°C								
Overcoating Time	2 hours. Minimum based on normal conditions.								
Cleaning	Wash all equipment immediately after use with clean water								

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
 Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

ODOUR-LESS CHÙI RỬA VƯỢT TRỘI & KHÁNG KHUẨN

Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.
Packing	1 Liter, 5 Liters and 15 Liters Containers
Precaution	<p>Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc.</p> <p>The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc.</p> <p>Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.</p> <p>For an optimal easy-wash effect, the paint film should be fully dried in 5 days before use. The easy-wash effect will be better if the stains are removed earlier.</p> <p>The stains on wall can be removed by soft tower with diluted detergent or disk washing liquid.</p>
NOTE	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com