

PRODUCT DATA SHEET

TEXKOTE

Description	Special Acrylic Emulsion giving three dimensional polymeric surface coating by spraying.
Type	Acrylic Emulsion
Uses	As a decorative / protective texture body coat for architectural surfaces under Interior and exterior condition such as: - Cement plasters - Brickworks - Fiberboards ... - Concrete - Primed wood
Finish	Matt Color: White
Features	- Excellent mechanical film properties such as film hardness, adhesion, scratch and abrasion resistance - Excellent algae and fungi resistance - Resistance to mud cracking tendency - Combination with topcoat, Texkote provides outstanding weathering property, high degree water repellency, good alkali resistance and Anti-dirt collection - Easy application with variation in pattern and shape of the film by means of application method - Comply with National technical regulation QCVN 08:2020/BCT on the limits of Lead content in paints. 
APPLICATION DATA	
Surface Preparation	Surface preparation should thoroughly done: Treatment with ANTI - FUNGUS SOLUTION is necessary for fungus growth area. Surface should be clean, dry and stable before application. - Masonry: below 16% by Protimeter Mini BLD 2000 Moisture meter below 60% by Lutron MS-7003 Moisture meter
Application Methods	Air spray
Paint Consumption	Theoretical: 0.7 - 1.5 m ² /liter depending on pattern desired
Dilution	For better result, no dilution is recommended. If need, use clean water, not more than 3%.

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

TEXKOTE

Spray Application	<u>Air Spray</u>
	Delivery Pressure (kg/cm ²) 2.5 - 4.5
	Tip size at 60° angle 4.5 or 6 mm
	Spray distance from substrate 1 foot
	Dilution 3% maximum
	To obtain "head-cut" pattern, roller should be used to press down the paint film when it is in semi-dry condition (about 10 - 15 minutes after application)
Overcoating Time	72 hours. Minimum
Cleaning	Wash all equipment immediately after use with clean water
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.
Packing	18 Liters Containers
Precaution	Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc. The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc. Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid directly contacting with sensitive skin. Use appropriate protective equipment.
NOTE	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam

Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com