

---

**PRODUCT DATA SHEET**


---

## ODOUR-LESS BÓNG SANG TRỌNG

|                    |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                       |
|--------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Description</b> | <p>ODOUR-LESS BÓNG SANG TRỌNG is a premium interior paint that perfectly combines sophisticated beauty, excellent protection and easy cleaning. With a sheen and a smooth paint film, this product not only brings a luxurious appearance but also protects your home with advanced technologies.</p> <p>EZWash Technology: Paint film is easy to be cleaned up because they cannot penetrate deeply into the paint film once it has fully dried.</p> <p>Colour Guard Technology: Guarantees the colours maintain the beauty and durability of the house's wall colour over time</p> <p>Anti-bacterial: Effectively resists harmful bacteria, creating a safe and clean living environment for the family</p>                                                                                                                                                                                                                                                                                                                                         |
| <b>Type</b>        | Modified Acrylic Emulsion                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             |
| <b>Uses</b>        | <p>It is ideal for interior walls such as:</p> <ul style="list-style-type: none"> <li>- Cement plasters                      - Brickworks                      - Gypsum board</li> <li>- Concrete                                - Primed wood                      - Fiberboards ...</li> </ul>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                      |
| <b>Finish</b>      | <p>Sheen</p> <p>Colour: Wide range of attractive colours as per colour card. Special colours on request.</p>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          |
| <b>Features</b>    | <ul style="list-style-type: none"> <li>- The paint film is sheen and smooth, bringing a luxurious beauty to your home.</li> <li>- Excellent washability with EZWash Technology</li> <li>- The paint film long-lasting remains vibrantly beautiful with Colour Guard Technology</li> <li>- Anti-bacterial effective against common bacteria such as E. Coli, Staphylococcus Aureus, Salmonella typhimurium, Shigella flexneri, Pseudomonas aeruginosa, Klebsiella pneumoniae, Listeria monocytogenes.</li> <li>- Excellent coverage and hiding power.</li> <li>- Extra low odour during application and after drying.</li> <li>- Anti-fungus properties</li> <li>- Excellent adhesion on stable substrates</li> <li>- Non-toxic, APEO free, does not contain Lead, Mercury, Chrome, Mercury and heavy metals</li> <li>- Low VOCs (containing &lt; 25g/L VOC, meeting the VOC requirement)</li> <li>- Green Label Certificate</li> <li>- Comply with National technical regulation QCVN 08:2020/BCT on the limits of Lead content in paints.</li> </ul> |



### NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Hung Ward, Dong Nai City, Vietnam  
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

[www.nipponpaint.com](http://www.nipponpaint.com)

# ODOUR-LESS BÓNG SANG TRỌNG

| APPLICATION DATA                           |                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           |                                         |               |                       |               |          |             |
|--------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------|---------------|-----------------------|---------------|----------|-------------|
| <b>Surface Preparation</b>                 | <p>Surface must be clean, dry, and stable.</p> <p><b><u>Suggested Treatment:</u></b></p> <p><u>Dirt/Powder:</u> Clean with damp cloth and remove loose powder. Mild detergent may be used.</p> <p><u>Old Paint/Plaster/Skimcoat:</u> Unstable old film / substrate should be removed by chisel, scraper, power grinder whichever is appropriate. Uneven substrates must be re-plastered with an approved putty / skimcoat.</p> <p><u>Moisture:</u> High moisture will cause paint defect. Observe the following level prior to painting:</p> <ul style="list-style-type: none"> <li>- Masonry: below 16% by Protimeter Mini BLD 2000 Moisture meter<br/>below 60% by Lutron MS-7003 Moisture meter</li> </ul> <p>All water seepage must be checked and repaired.</p> <p><u>Algae/Fungus:</u> Remove by chisel or scraper and treat with ANTI - FUNGUS SOLUTION. Rinse again with clean water and dry.</p> <p><u>Oil/Grease:</u> Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace.</p> |                                         |               |                       |               |          |             |
| <b>Application Methods</b>                 | Brush, roller or airless spray                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                            |                                         |               |                       |               |          |             |
| <b>Paint Consumption</b>                   | Theoretical: 9.0 - 12.0 m <sup>2</sup> / liter (30 - 40 microns DFT)                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                      |                                         |               |                       |               |          |             |
| <b>Dilution</b>                            | <p>Not more than 15% of clean water if required</p> <table> <tr> <td>Roller &amp; brush</td><td>- 15% maximum</td></tr> <tr> <td>Airless Spray</td><td>- 10% maximum</td></tr> </table>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                   | Roller & brush                          | - 15% maximum | Airless Spray         | - 10% maximum |          |             |
| Roller & brush                             | - 15% maximum                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             |                                         |               |                       |               |          |             |
| Airless Spray                              | - 10% maximum                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                             |                                         |               |                       |               |          |             |
| <b>Spray Application</b>                   | <p><u>Airless Spray</u></p> <table> <tr> <td>Delivery Pressure (kg/cm<sup>2</sup>)</td><td>120 - 150</td></tr> <tr> <td>Tip size at 60° angle</td><td>0.017"</td></tr> <tr> <td>Dilution</td><td>10% maximum</td></tr> </table>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           | Delivery Pressure (kg/cm <sup>2</sup> ) | 120 - 150     | Tip size at 60° angle | 0.017"        | Dilution | 10% maximum |
| Delivery Pressure (kg/cm <sup>2</sup> )    | 120 - 150                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                 |                                         |               |                       |               |          |             |
| Tip size at 60° angle                      | 0.017"                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                    |                                         |               |                       |               |          |             |
| Dilution                                   | 10% maximum                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                               |                                         |               |                       |               |          |             |
| <b>Recommended Painting System</b>         | <ul style="list-style-type: none"> <li>- 1 - 2 coats NIPPON INTERIOR PUTTY</li> <li>- 1 coat ODOUR-LESS SEALER</li> <li>- 2 coats ODOUR-LESS BÓNG SANG TRỌNG</li> </ul>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                   |                                         |               |                       |               |          |             |
| <b>Recommended Film Thickness per coat</b> | 30 - 40 microns DFT (Dry Film Thickness) per coat for standard application                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                |                                         |               |                       |               |          |             |
| <b>Drying Time</b>                         | Surface dry: 30 minutes at 30°C                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           |                                         |               |                       |               |          |             |
| <b>Overcoating Time</b>                    | 2 hours. Minimum based on normal conditions.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              |                                         |               |                       |               |          |             |
| <b>Post Treatment</b>                      | As the paint film is elastic, masking tapes used to protect surfaces not to be painted, e.g. door and window frames, should be removed with a knife or cutter.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                            |                                         |               |                       |               |          |             |
| <b>Cleaning</b>                            | Wash all equipment immediately after use with clean water                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                 |                                         |               |                       |               |          |             |

## NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Hung Ward, Dong Nai City, Vietnam  
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

[www.nipponpaint.com](http://www.nipponpaint.com)

## ODOUR-LESS BÓNG SANG TRỌNG

|                   |                                                                                                                                                                                                                                                                                                                                                                                                                                                    |
|-------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Storage</b>    | Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.                                                                                                                                                                                                                                                                                                                                     |
| <b>Packing</b>    | 1 Liter, 5 Liters & 15 Liters Containers                                                                                                                                                                                                                                                                                                                                                                                                           |
| <b>Precaution</b> | <p>Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc.</p> <p>The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc.</p> <p>Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.</p> |
| <b>NOTE</b>       | <i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales &amp; Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>                                                                                 |

### NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Hung Ward, Dong Nai City, Vietnam  
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

[www.nipponpaint.com](http://www.nipponpaint.com)