

PRODUCT DATA SHEET

WP 200 PLUS

Description	<p>WP 200 PLUS is a premium exterior water-proofing paint, formulated with Modified Nano Acrylic Emulsion combined with HydroGuard Technology, providing superior protection for vertical wall surfaces against water penetration from the applied side for vertical surfaces.</p> <p>WP 200 PLUS has high elasticity, effectively covering small cracks.</p> <p>The product does not require mixing with cement, making it easy to apply.</p>
Type	Modified Nano Acrylic Emulsion
Uses	<p>Premium grade emulsion with water-proofing and excellent protection for all exterior masonry surfaces such as:</p> <p>Cement plasters – Concrete – Brickworks...</p>
Finish	<p>Sheen</p> <p>Colour: Wide range of attractive colours as per colour card.</p>
Features	<ul style="list-style-type: none"> - Superior water resistance - Excellent to Alkaline & Efflorescence properties - Excellent adhesion on stable surfaces - Resistance to Fungus & Algae growth - Easy to apply - With high elasticity, the paint film can cover hairline cracks at a dry film thickness of 150 microns - Low VOCs (containing < 50g/L VOC, meeting the VOC requirement) - Non-toxic, does not contain Lead, Mercury and heavy metals - Comply with National technical regulation QCVN 08:2020/BCT on the limits of Lead content in paints 
Application Data	
Surface Preparation	<p>Surface must be clean, dry, and stable.</p> <p>Suggested Treatment:</p> <p><u>Dirt/Powder</u>: High pressure water wash. Mild detergent may be used. For very powdery surface, apply a coat of HITEX 5180 SEALER after cleaning.</p> <p><u>Old Paint/Plaster</u>: Unstable old film / substrate should be removed by chisel, scraper, power grinder whichever is appropriate.</p> <p><u>Moisture</u>: High moisture will cause paint defect. Observe the following level prior to painting:</p> <p><u>Masonry</u>: below 6% by Sovereign 1150 Moisture meter below 16% by Protimeter Mini BLD 2000 Moisture meter</p>

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Hung Ward, Dong Nai City, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

WP 200 PLUS

	<p>below 60% by Lutron MS-7003 Moisture meter</p> <p>All water seepage must be checked and repaired.</p> <p><u>Algae/Fungus:</u> Remove by high pressure wash or by chisel, scraper and treat with NIPPON ANTI- FUNGUS SOLUTION. Rinse again with clean water and dry.</p> <p><u>Oil/Grease:</u> Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace</p>
Application Methods	Brush, roller or airless spray
Paint Consumption	Theoretical: 7.5 m ² / Kg (50 µm DFT)
Dilution	No dilution needed.
Spray Application	<p style="text-align: right;">Airless Spray</p> <p>Delivery Pressure (kg/cm²) 120 -150</p> <p>Tip size at 60° angle 0.017"</p> <p>Dilution 5% maximum</p>
Recommended Painting System	2 coats WP 200 PLUS
Recommended Film Thickness per coat	50 – 60 microns DFT (Dry Film Thickness) per coat for standard application
Drying Time	Surface dry: 30 minutes at 30°C
Overcoating Time	2 hours. Minimum based on normal conditions
Post Treatment	As the paint film is elastic, masking tapes used to protect surfaces not to be painted, e.g. door and window frames, should be removed with a knife or cutter after painting
Cleaning	Wash all equipment immediately after use with clean water
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C
Packing	6 Kg & 18 Kg Containers
Precaution	<p>Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc.</p> <p>The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc.</p> <p>Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.</p>
NOTE	<i>The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.</i>

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Hung Ward, Dong Nai City, Vietnam

Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com